



1468 West Hospital Road  
 Paoli, Indiana U.S.A. 47454-9215  
 voice: 812/723-0704  
 fax: 812/723-5998  
 internet: www.inliner.net

**TECHNICAL DATA SHEET – InTech 72-20 Enhanced Polyester Resin**

InTech 72-20 is a physical strength enhanced, promoted, thixotropic, rigid, corrosion resistant, polyester resin. It is specifically formulated to resist various chemical solutions, as well as municipal sewage and water when manufactured according to cured-in-place techniques for the relining of pipes. This resin has been tested and has passed the requirements for retention of physical properties and weight gain when exposed to corrosive media to ASTM test procedures D5813 and F1216. It has also been tested according to ASTM D-2990 for Flexural Creep. Data on these tests and any corrosion recommendations will be supplied upon request. Resins manufacturers for Inliner meeting this specification are as follows: AOC LLC, Ashland Specialty Chemical Company, Interplastic Corporation and Reichhold Inc.

**TECHNICAL DATA**

**LIQUID RESIN PROPERTIES**

Viscosity, Brookfield Model RV @ 77°F (25°C), #4 spindle @ 20 rpm, cps	4,000-6,000
Thixotropic Index	4.0 – 5.0
Gel time run in a 140°F (60°C) water bath, catalyzed with 0.1 phr of Perkadox 16 and 0.5 phr of Trigonox 42S, minutes	8-14
Stability at: 72°F (22.0°C)	≥ 24 hours
Non-Volatile, %	65 – 70
Specific Gravity	1.2 – 1.3

**TYPICAL PROPERTIES OF A 6 MM FELT LAMINATE**

Flexural Strength, ASTM D-790	7,000 psi	48 MPa
Flexural Modulus, ASTM D-790	625,000 psi	4,309 MPa
Tensile Strength, ASTM D-638	4,200 psi	29 MPa
Tensile Modulus, ASTM D-638	700,000 psi	4,826 MPa
Tensile Elongation, ASTM D-638	0.8 %	0.8 %
Barcol Hardness (934-1), ASTM D-2583	35 - 45	35 - 45

All specification and properties shown are approximate. Specifications and properties of material delivered may vary slightly from those given above. Inliner Technologies, Inc. makes no representations of fact regarding the material except those specified above. No person has any authority to bind Inliner Technologies, Inc. to any representation except those specified above. Final determination of the suitability of the material for the use contemplated is the sole responsibility of the Buyer. Inliner Technologies, Inc. sales representatives will assist in developing procedures to fit individual requirements.